



THICKER THERMAL INSULATOR PAD PREVENTS ELECTRICAL SHORTS IN AUTOMOTIVE ELECTRONICS APPLICATIONS

Tgard™ 500 is a medium thermal performance insulator pad consisting of a ceramic filled high temperature silicone rubber coated on electrical grade fiberglass.

Tgard™ 500 is designed for applications that require additional thickness to prevent electrical shorts from stamped aluminum heatsinks used in switching mode power supplies (SMPS) and debris from aluminum castings used in automotive motor controls.

Tgard™ 500 is used in applications that require interface of 2.4°C/watt or higher on a TO-220 mounted @ 50 psi pressure.

FEATURES AND BENEFITS

- High breakdown voltage of >6,000 volts AC
- Thermal resistance of 0.45°C-in²/watt at 50 psi
- Thermal resistance of 0.35°C-in²/watt at 400 psi
- Thick enough to encapsulate burrs of stamped heatsinks

APPLICATIONS

- Automotive motor controls
- Switching mode power supplies
 - Stamped aluminum heatsinks

global solutions: local support.™

Americas: +1.800.843.4556

Europe: +49.8031.2460.0

Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com

www.lairdtech.com/thermal

Thermally Conductive Insulators

PROPERTY	TEST METHOD	METRIC VALUES		IMPERICAL VALUES			
ELECTRICAL PROPERTIES							
Dielectric With Standard Voltage 50mm probe for 30 sec.	ASTM D149	4,500 volts AC		4,500 volts AC			
Dielectric Breakdown Voltage 50mm probe	ASTM D149	>6,000 volts AC		>6,000 volts AC			
Volume Resistivity	ASTM D257	>10 ¹² ohm-cm		>10 ¹² ohm-in			
Dielectric Constant @ 1 MHz	ASTM D257	3.3		3.3			
Electrical RTI Temperature rating	UL 746D	150°C		302°F			
MECHANICAL PROPERTIES							
Thickness		0.23 mm		0.009 inch			
Hardness	ASTM D2240	85 Shore A		85 Shore A			
Tensile Strength	ASTM D412	1.3 kpsi		9 mPa			
Elongation @ 45° to Warp/Fill	ASTM D412	20%		20%			
Elongation along width or length	ASTM D412	5%		5%			
Operating Temperature Range		-60 - 180°C		-76 - 357°F			
Color		Brown		Brown			
UL Flammability Rating	UL 94	V-0		V-0			
PRESSURE, PSI (KPA)	UNITS	10 (69)	25 (172)	50 (345)	100 (689)	200 (1379)	400 (2758)
TOTAL THERMAL RESISTANCE							
Modified ASTM D5470	°C-in ² /watt	0.6	0.55	0.45	0.40	0.35	0.35
Modified ASTM D5470	°C-cm ² /watt	3.9	3.2	2.9	2.6	2.3	2.3
TO-220	°C/watt	3.2	2.9	2.4	2.2	2.0	2.0

STANDARD THICKNESS: 9 mils (0.229mm)

DIE CUT PARTS: Standard and custom configurations available

PRESSURE SENSITIVE ADHESIVE: Single side adhesive available on request

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

THR-DS-TGARD-500 0710

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies Terms and Conditions of Sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2010 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. A15173-00 REV A, 7/16/09